

FEATURE CARATTERISTICA DATEN CARACTÉRISTIQUE		TECHNICAL FEATURES CARATTERISTICHE TECNICHE TECHNISCHE DATEN CARACTÉRISTIQUES TECHNIQUES	STANDARD NORMA NORM NORME	ESTABLISHED LIMITS LIMITI PREVISTI VORGESEHENE GRENZWERTE LIMITES ÉTABLIES		L'ALTRA PIETRA®
REGULARITY REGOLARITÀ REGELMÄßIGKEIT RÉGULARITÉ		LENGHT AND WIDTH LUNGHEZZA E LARGHEZZA LÄNGE UND BREITE LONGUEUR ET LARGEUR	ISO 10545-2	± 0.6 %	± 2 mm	COMPLYING CONFORME ERFÜLLT CONFORME
		THICKNESS SPESSORE DICKE ÉPAISSEUR	ISO 10545-2	± 5.0 %	± 0.5 mm	COMPLYING CONFORME ERFÜLLT CONFORME
		RECTANGULARITY ORTOGONALITÀ RECHTWINKLIGKEIT PERPENDICULARITÉ	ISO 10545-2	± 0.5 %	± 2 mm	COMPLYING CONFORME ERFÜLLT CONFORME
		STRAIGHTNESS OF SIDES RETTILINEITÀ DEGLI SPIGOLI GERADLINIGKEIT DER KANTEN RECTITUDE DES ARÊTES	ISO 10545-2	± 0.5 %	± 1.5 mm	COMPLYING CONFORME ERFÜLLT CONFORME
		SURFACE FLATNESS PLANARITÀ EBENFLÄCHIGKEIT PLANEITE DE SURFACE	ISO 10545-2	± 0.5 %	± 2 mm	COMPLYING CONFORME ERFÜLLT CONFORME
STRUCTURAL STRUTTURALE STRUKTURELL STRUCTURAL		WATER ABSORPTION ASSORBIMENTO D'ACQUA WASSERAUFNAHME ABSORPTION D'EAU	ISO 10545-3	≤ 0.5 %		COMPLYING CONFORME ERFÜLLT CONFORME
		BREAKING STRENGHT SFORZO DI ROTTURA BRUCHFESTIGKEIT FORCE DE RUPTURE	ISO 10545-4	≥ 1300 N		>10000 N
		MODULUS OF RUPTURE MODULO DI ROTTURA BRUCHMODUL MODULE DE RUPTURE	ISO 10545-4	≥ 35 N/mm²		≥ 35 N/mm²
SURFACE SUPERFICIE OBERFLÄCHE SURFACE		ABRASION RESISTANCE RESISTENZA ALL'ABRASIONE ABRIEBFESTIGKEIT RESISTANCE A L'ABRASION	ISO 10545-7	CLASS DECLARED CLASSE DICHIARATA KLASSE ERKLÄRT CLASSE DÉCLARÉ		A Grigia: 3, 1500 rp S S Beige: 4, 2100 rp C Light: 4, 12000 rp C Dark: 3, 1500 rp
THERMAL HYGROMETRIC TERMO IGROMETRICHE THERMAL HYGROMETRISCH THERMIQUE HYGROMÉTRIQUE		LINEAR THERMAL-EXPANSION DILATAZIONE TERMICA LINEARE LINEARER WÄRMEAUSSDEHNUNG DILATATION THERMIQUE LINEAIRE	ISO 10545-8	VALUE DECLARED VALORE DICHIARATO ERKLÄRTER WERT VALEUR DÉCLARÉE		α ≤ 9 · 10 ⁻⁶ °C
		THERMAL SHOCK RESISTANCE RESISTENZA AGLI SBALZI TERMICI WIDERSTANDSFÄHIGKEIT GEGEN TEMPERATURSCHWANKUNGEN RÉSISTANCE AUX ÉCARTS DE TEMPÉRATURE	ISO 10545-9	TEST PASSED TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		GUARANTEED GARANTITO GARANTIERT GARANTI
		FROST RESISTANCE RESISTENZA AL GELO FROSTBESTÄNDIGKEIT RÉSISTANCE AU GEL	ISO 10545-12	TEST PASSED TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		GUARANTEED GARANTITO GARANTIERT GARANTI
CHEMICAL CHIMICA CHEMISCH CHIMIQUE		RESISTANCE TO CHEMICALS (ACIDS, BASES AND SALTS) RESISTENZA ALL'ATTACCO CHIMICO (ACIDI, BASI E SALI) CHEMIKALIENBESTÄNDIGKEIT (SÄUREN, BASIS UND SALZ) RESISTANCE A L'ATTAQUE CHIMIQUE (ACIDES, BASES ET SELS)	ISO 10545-13	UB MINIMUM UB MINIMO UB MINIMUM UB MINIMUM		A HA LA GUARANTEED GARANTITO GARANTIERT GARANTI

PIATRA ONLINE

[+40318222333](tel:+40318222333) / office@piatraonline.com

Aleea Teisani nr.137A, sector 1, 014034 Bucuresti

		RESISTANCE TO STAINS RESISTENZA ALLE MACCHIE FLECKENBESTÄNDIGKEIT RESISTANCE AUX TACHES	ISO 10545-14	≥ 3	5 GUARANTEED 5 GARANTITO 5 GARANTIERT 5 GARANTI
SAFETY SICUREZZA SICHERHEIT SÉCURITÉ		SKID RESISTANCE RESISTENZA ALLO SCIVOLAMENTO RUTSCHHEMMUNG RÉSISTANCE AU GLISSEMENT	DIN 51130	VALUE DECLARED VALORE DICHIARATO ERKLÄRTER WERT VALEUR DÉCLARÉE	R11
			DIN 51097		A+B
		REACTION TO FIRE REAZIONE AL FUOCO REAKTION ZUM FEUER RÉACTION AU FEU	EN 13501-1	CLASS DECLARED CLASSE DICHIARATA KLASSE ERKLÄRT CLASSE DÉCLARÉ	A1 FL / A1

Compliant with standards EN 14411 (ISO 13006) annex G group Bla
Conforme alla norma EN 14411 (ISO 13006) Appendice G gruppo Bla