

FEATURE CARATTERISTICA DATEN CARACTÉRISTIQUE		TECHNICAL FEATURES CARATTERISTICHE TECNICHE TECHNISCHE DATEN CARACTÉRISTIQUES TECHNIQUES	STANDARD NORMA NORM NORME	ESTABLISHED LIMITS LIMITI PREVISTI VORGESEHENE GRENZWERTE LIMITES ÉTABLIES		L'ALTRA PIETRA®
REGULARITY REGOLARITÀ REGELMÄßIGKEIT RÉGULARITÉ		LENGHT AND WIDTH LUNGHEZZA E LARGHEZZA LÄNGE UND BREITE LONGUEUR ET LARGEUR	ISO 10545-2	± 0.6 %	± 2 mm	COMPLYING CONFORME ERFÜLLT CONFORME
		THICKNESS SPESSORE DICKE ÉPAISSEUR	ISO 10545-2	± 5.0 %	± 0.5 mm	COMPLYING CONFORME ERFÜLLT CONFORME
		RECTANGULARITY ORTOGONALITÀ RECHTWINKLIGKEIT PERPENDICULARITÉ	ISO 10545-2	± 0.5 %	± 2 mm	COMPLYING CONFORME ERFÜLLT CONFORME
		STRAIGHTNESS OF SIDES RETTILINEITÀ DEGLI SPIGOLI GERADLINIGKEIT DER KANTEN RECTITUDE DES ARETES	ISO 10545-2	± 0.5 %	± 1.5 mm	COMPLYING CONFORME ERFÜLLT CONFORME
		SURFACE FLATNESS PLANARITÀ EBENFLÄCHIGKEIT PLANEITÉ DE SURFACE	ISO 10545-2	± 0.5 %	± 2 mm	COMPLYING CONFORME ERFÜLLT CONFORME
STRUCTURAL STRUTTURALE STRUKTURELL STRUCTURAL		WATER ABSORPTION ASSORBIMENTO D'ACQUA WASSERAUFNAHME ABSORPTION D'EAU	ISO 10545-3	≤ 0.5 %		COMPLYING CONFORME ERFÜLLT CONFORME
		BREAKING STRENGHT SFORZO DI ROTTURA BRUCHFESTIGKEIT FORCE DE RUPTURE	ISO 10545-4	≥ 1300 N		≥ 10000 N
		MODULUS OF RUPTURE MODULO DI ROTTURA BRUCHMODUL MODULE DE RUPTURE	ISO 10545-4	≥ 35 N/mm²		≥ 35 N/mm²
THERMAL HYGROMETRIC TERMO IGROMETRICHE THERMAL HYGROMETRISCH THERMIQUE HYGROMÉTRIQUE		LINEAR THERMAL-EXPANSION DILATAZIONE TERMICA LINEARE LINEARER WÄRMEUSDEHNUNG DILATATION THERMIQUE LINEAIRE	ISO 10545-8	VALUE DECLARED VALORE DICHIARATO ERKLÄRTER WERT VALEUR DÉCLARÉE		$\alpha \leq 7 \cdot 10^{-6} \text{ }^{\circ}\text{C}$
		THERMAL SHOCK RESISTANCE RESISTENZA AGLI SBALZI TERMICI WIDERSTANDSFÄHIGKEIT GEGEN TEMPERATURSCHWANKUNGEN RÉSISTANCE AUX ÉCARTS DE TEMPÉRATURE	ISO 10545-9	TEST PASSED TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		GUARANTEED GARANTITO GARANTIERT GARANTI
		FROST RESISTANCE RESISTENZA AL GELO FROSTBESTÄNDIGKEIT RÉSISTANCE AU GEL	ISO 10545-12	TEST PASSED TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		GUARANTEED GARANTITO GARANTIERT GARANTI
		REACTION TO FIRE REAZIONE AL FUOCO REAKTION ZUM FEUER RÉACTION AU FEU	EN 9239-1	TEST PASSED TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		A1fl
LIGHT LUCE LICHT LUMIÈRE		COLOUR RESISTANCE TO LIGHT EXPOSURE RESISTENZA DEI COLORI ALLA LUCE LICHTTECHTHEIT DER FARBEN RÉSISTANCE DES COULEURS À LA LUMIÈRE	DIN 51094	NO NOTICEABLE COLOUR MODIFICATIONS. ASSENZA DI APPREZZABILI ALTERAZIONI DI COLORE. KEIN SICHTBARE FARBVERÄNDERUNGEN AUFWEISEN. AUCUN ALTERATIONS APPRÉCIABLES DE COULEUR.		COMPLYING CONFORME ERFÜLLT CONFORME

PIATRA ONLINE

[+40318222333](tel:+40318222333) / office@piatraonline.com

Aleea Teisani nr.137A, sector 1, 014034 Bucuresti

CHEMICAL CHIMICA CHEMISCH CHIMIQUE		RESISTANCE TO CHEMICALS (ACIDS, BASES AND SALTS) RESISTENZA ALL'ATTACCO CHIMICO (ACIDI, BASI E SALI) CHEMIKALIENBESTÄNDIGKEIT (SÄUREN, BASIS UND SALZ) RESISTANCE A L'ATTAQUE CHIMIQUE (ACIDES, BASES ET SELS)	ISO 10545-13	UB MINIMUM UB MINIMO UB MINIMUM UB MINIMUM	GA GLA GHA GUARANTEED GARANTITO GARANTIERT GARANTI
		RESISTANCE TO STAINS RESISTENZA ALLE MACCHIE FLECKENBESTÄNDIGKEIT RESISTANCE AUX TACHES	ISO 10545-14	≥ 3	5 GUARANTEED 5 GARANTITO 5 GARANTIERT 5 GARANTI
SAFETY SICUREZZA SICHERHEIT SÉCURITÉ		SKID RESISTANCE RESISTENZA ALLO SCIVOLAMENTO RUTSCHHEMMUNG RÉSISTANCE AU GLISSEMENT	DIN 51130	VALUE DECLARED VALORE DICHIARATO ERKLÄRTER WERT VALEUR DÉCLARÉE	R11

Compliant with standards EN 14411 (ISO 13006) annex G group Bla
Conforme alla norma EN 14411 (ISO 13006) Appendice G gruppo Bla